

ZDX 众德祥
Feedstock MIM

产品 Product	Fe02Ni B (通用型) Fe02Ni B (For general-purpose)									
产品描述 Product description	金属注射成型原料 Feedstock for metal injection moulding.									
收缩率 Oversize factor	Min. 1.213	Average 1.216			Max. 1.219					
熔体流动指数 MFI g/10min	min. 400	Average 800			Max. 1200		DIN EN ISO 1133 (190°C/21.6kg)			
烧结后典型成分 (按重量百分比计算) Typical composition after Sintering		Fe	C	Cr	Ni	Mo	Mn	Si	S	P
	>	-	0.4	-	1.5	-	-	-	0.0	0.0
	<	Bal.	0.6	-	2.5	-	-	-	0.03	0.035

<div> <div>注射工艺</div> <div>Injection process</div> </div>	建议注射温度	Zone1	Zone 2	Zone 3	Zone 4	Nozzle
	Recommended injection temperature	185°C	185°C	175°C	150°C	190°C
	建议模具温度	90-125°C				
	Recommended injection temperature					
	参考生坯密度区间	4.82-4.88 g/cm ³				
	<p>其余注塑工艺参数受到产品形状及要求影响较大，故未写出。</p> <p>需要注意的是，注塑工艺的设定对于产品的生坯密度有着较大的影响，而这也可能导致产品最终尺寸和其他要求不符使用者的期望。</p> <p>Other injection molding process parameters are greatly affected by product shape and requirements, so they are not written out.</p> <p>It should be noted that the setting of injection molding process has a great influence on the green density of the product, which may also cause the final size of the product and other requirements do not meet the user's expectations.</p>					

脱脂工艺 Debinding process	脱脂酸 Debinding acid	98% HNO ₃
	脱脂温度 Debinding temperature	100-150°C
	脱脂时间 Debinding time	取决于零件厚度 Depending on part thickness (e.g. 3 mm part approx. 3h)
	脱脂工艺 Debinding process	当生坯最低脱脂率 达到 9.8% 时，可以终止脱脂制程 When the minimum debinding rate of green part when it reaches 9.8%, the debinding process can be terminated.
烧结工艺 Sintering process	烧结气氛 Sintering atmosphere	氩气烧结 100% dry argon
	烧结载具 Sintering substrate	氧化铝陶瓷片 Non-metallic base (e.g. Al ₂ O ₃)
	负压脱脂 Negative pressure degreasing	从室温升高至 600°C 过程中，采用有多段持温的负压脱脂，以确保剩余粘结剂能被脱脂干净，总时间 450min 左右。 From room temperature to 600 °C, vacuum debinding with multi-stage holding temperature is used to ensure that the remaining binder can be removed completely, and the total time is around 450 min.
	真空烧结 Vacuum sintering	从 600°C 以 3°C/min 升温至 850 摄氏度持温一段时间进行真空内烧，目的是确保产品碳含量在合理区间。 From 600 °C to 850 °C at 3 °C / min and holding for a period of time, the vacuum internal sintering is carried out to ensure that the carbon content of the product is in a reasonable range .
	分压烧结 Partial pressure sintering	从 850°C 以 3°C/min 升温至 1050°C 后短暂持温，之后以同样的升温速度升高至 1260°C，使得材料致密化，最后随炉冷却。 From 850 °C to 1050 °C at 3 °C/ min, holding for a short time, and then it was raised to 1260 °C at the same heating rate for material densify, and finally cooled with the furnace.
保质期 Shelf life	如果储存得当：12 个月，防止原料受潮。 If stored appropriately: 12 months. Protect feedstock against moisture.	

免责声明：本物性表仅基于我们的知识和经验得出，具有一定的参考意义，但由于影响产品最终要求和性能的因素众多，并不能完全排除使用者由于各种原因导致与期望不符的现象。

Disclaimer: This datasheet is only based on our knowledge and experience, which has certain reference significance. However, it cannot completely exclude the user's non-compliance with expectations due to various reasons, because there exist many uncontrolled factors affecting the final requirements and performance of the products.